



Light- and/or Heat-Curable Materials for Automotive Camera Module Assembly

- One-component formulations
- Solvent free and environmentally friendly materials
- Excellent adhesion to commonly used substrates in camera module assemblies
- Materials cure in seconds allowing faster processing and higher throughput
- Materials available for a variety of applications including active alignment, and barrel fixturing
- Very low shrinkage with excellent resistance to moisture and shock
- On-demand cures for a more efficient process
- Materials formulated with secondary heat- or moisture-cure for shadow areas available
- Possible to set up for in-line production processes
- Greater output and lower processing costs

Dymax light-curable adhesives are ideal for camera module assemblies found in passenger vehicles, trucks, off-road vehicles as well as in many other transportation-related applications. The adhesives cure on-demand in seconds with light, providing greater product yields in a much shorter assembly time. Materials are also available with secondary heat or moisture cure to accommodate designs with shadow areas.

Dymax materials are one-component, requiring no mixing, and solvent-free for a more environmentally friendly process. They provide excellent adhesion to substrates typically used in the manufacture of camera modules and electronic device housings, and can withstand harsh conditions like temperature extremes, moisture, shock, and corrosive chemicals which automobiles are often exposed to.

Product Number	Features	Viscosity, cP	Durometer Hardness	Tensile at Break, MPa [psij]	Modulus of Elasticity, MPa [psij]	Shrinkage, %
Positioning Adhesives						
9900-AA	UV/Visible light cure and/or heat cure epoxy; low shrinkage; moisture and thermal cycle resistant; cold storage/cold ship; low temperature heat cure	43,492	D92	57.7 [8,373]	1,962 [284,578]	
9906-AA	Very low volumetric shrinkage and water absorption; greater depth of cure; UV/Visible light cure and/or heat cure epoxy; low shrinkage; moisture and thermal cycle resistant; cold storage/cold ship; low temperature heat cure	86,000	D94	36.7 [5,328]	3,983 [578,000]	1.1 Volumetric
Plastic/Structural-Bonding Adhesives						
6-621	UV/Visible light cure with secondary heat cure; activator cure; hard, clear bonds; bonds multiple substrates	800	D80	22 [3,200]	550 [80,500]	0.4 Linear
3094-T-REV-A	Low stress plastic bonder; UV/Visible light cure; low shrinkage	11,750	D65	14 [2,800]	698 [101,300]	0.7 Linear
3094-GEL-REV-A	Low stress plastic bonder; UV/Visible light cure; low shrinkage	30,000	D67	12.4 [1,800]	179 [26,000]	0.5 Linear
Encapsulants						
9008	UV/Visible light cure; remains flexible to -40°C; moisture resistant	4,500	D35	10 [1,500]	45 [6,500]	1.2 Linear
9014	UV light cure with secondary moisture cure; blue fluorescing; flexible	18,000	A70	8.2 [1,200]	119 [17,300]	1.8 Linear
9037-F	UV/Visible light cure with secondary heat cure; flexible; blue fluorescing; moisture and thermal resistance	55,000	D40	5.8 [850]	6.2 [900]	2.2 Linear
9102	UV/Visible light cure with secondary moisture cure; flexible; blue fluorescing; moisture and thermal resistance	17,000	D30-D50	4.8 [703]	18.4 [2,670]	2.0 Linear
Conformal Coatings						
9483	UV/Visible light cure with secondary moisture cure; excellent chemical and thermal shock resistance; blue fluorescing	750	D60	16.2 [2,350]	274 [40,000]	2.0 Linear



www.dymax.com

Americas

USA | +1.860.482.1010 | info@dymax.com

Europe

Germany | +49 611.962.7900 | info_de@dymax.com
Ireland | +353 21.237.3016 | info_ie@dymax.com

Asia

Singapore | +65.67522887 | info_ap@dymax.com
China | +86.755.83485759 | dymaxasia@dymax.com
Hong Kong | +852.2460.7038 | dymaxasia@dymax.com
Korea | +82.31.608.3434 | info_kr@dymax.com

©2021 Dymax Corporation. All rights reserved. All trademarks in this guide, except where noted, are the property of, or used under license by, Dymax Corporation, U.S.A.

Technical data provided is of a general nature and is based on laboratory test conditions. Dymax does not warrant the data contained in this bulletin. Any warranty applicable to the product, its application and use is strictly limited to that contained in Dymax standard Conditions of Sale published on our website. Dymax does not assume responsibility for test or performance results obtained by users. It is the user's responsibility to determine the suitability for the product application and purposes and the suitability for use in the user's intended manufacturing apparatus and methods. The user should adopt such precautions and use guidelines as may be reasonably advisable or necessary for the protection of property and persons. Nothing in this communication shall act as a representation that the product use or application will not infringe on a patent owned by someone other than Dymax or act as a grant of license under any Dymax Corporation Patent. Dymax recommends that each user adequately test its proposed use and application before actual repetitive use, using the data in this communication as a general guideline.

AB017DA 12/22/2021